



## NACE TM-01-69 Test Cycle

Test Cycle-The TM-01-69 test cycle consists the following stages run at 70F and 50% humidity:

1. 10 minutes emersion in Mag Chloride solution
2. 50 minute air dry
3. Duration – 72 hours continuous
4. Panels are weighed and weight loss due corrosion is noted

Note: Full test report available upon request